

**INDIANA DEPARTMENT OF TRANSPORTATION  
OFFICE OF MATERIALS MANAGEMENT**

**QUANTITATIVE EXTRACTION OF ASPHALT AND GRADATION  
OF EXTRACTED AGGREGATE FROM HMA MIXTURES  
ITM No. 571-08T**

**1.0 SCOPE.**

- 1.1** This method of test covers the procedure for the quantitative determination of the asphalt/binder content and gradation of the extracted aggregate of HMA mixtures.
- 1.2** The HMA mixture is extracted with a suitable solvent, depending on the type of extraction apparatus used. The asphalt content is calculated by determining the difference of the weight (mass) of the HMA mixture and the extracted aggregate, fibers if used, and the fines recovered from the extracted solvent and water rinse, if required. The gradation of the extracted aggregate is then determined.
- 1.3** The values stated in either acceptable English or SI metric units are to be regarded separately as standard, as appropriate for a specification with which this ITM is used. Within the text, SI metric units are shown in parenthesis. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other, without combining values in any way.
- 1.4** This ITM may involve hazardous materials, operations, and equipment and may not address all of the safety problems associated with the use of the test method. The user of the ITM is responsible for establishing appropriate safety and health practices and determining the applicability of regulatory limitations prior to use.

**2.0 REFERENCES.**

**2.1 AASHTO Standards.**

- M 231 Weighing Devices Used in the Testing of Materials
- T 30 Mechanical Analysis of Extracted Aggregate
- T 164 Quantative Extraction of Bitumen from Bituminous Paving Mixtures

**2.2 ITM Standards.**

- 572 Dying HMA Mixtures
- 580 Sampling HMA

**3.0 TERMINOLOGY.** Definitions for terms and abbreviations shall be in accordance with the Department's Standard Specifications, Section 101.

**4.0 SIGNIFICANCE AND USE.** This ITM shall be used to determine the asphalt content and gradation of the extracted HMA mixture.

**5.0 APPARATUS.**

**5.1** Balance, a Class G2, in accordance with AASHTO M 231

**5.2** Electric skillet, with a thermostatic heat control capable of heating to 221°F (105°C)

**5.3** Oven, capable of maintaining the temperature at  $221 \pm 9^\circ\text{F}$  ( $105 \pm 5^\circ\text{C}$ )

**5.4** Pans and containers as needed

**5.5** Sieves, in accordance with AASHTO T 30

**5.6** Spatulas and trowels as needed

**5.7** Stiff bristle brush, 1 in. (25 mm) in diameter

**5.8** Thermometer, armored with a range of 100°F (40°C) to 450°F (230°C), readable to 5°F (2°C)

**5.9** Wash bottle

**6.0 REAGENTS.**

**6.1** Extraction Solvent

**6.2** Trichloroethylene, Reagent Grade conforming to ASTM D 4080

**7.0 SAFETY PRECAUTIONS.**

**7.1** The reagent solvents are toxic as shown below:

Reagent	Maximum Acceptable Concentration for 8 h Exposure, ppm
Extraction Solvent	Not Established
Trichloroethylene	10

- 7.2 Provide adequate ventilation and avoid inhalation of vapor. The ventilation fan shall be operating during the testing.
- 7.3 The exhaust from the vacuum pump shall be vented outside.
- 7.4 Trichloroethylene has a boiling point of 189°F (87°C). The Material Safety Data Sheet shall list the boiling point of the extraction solvent.
- 7.5 The extraction solvent shall be an approved solvent.

**8.0 SAMPLING.** Sampling shall conform to the requirements of ITM 580.

**9.0 PREPARATION OF SAMPLE.**

- 9.1 If the sample is not sufficiently soft to separate with a spatula or a trowel, place the sample in a large flat pan and heat to a maximum of  $221 \pm 9^{\circ}\text{F}$  ( $105 \pm 5^{\circ}\text{C}$ ) only until the sample may be handled. Separate the sample as uniformly as possible, using care not to fracture the mineral aggregate.
- 9.2 The approximate minimum size of the sample shall be in accordance with the following:

Mixture Designation	Minimum Weight (mass) of Sample, g
4.75 mm	1000
9.5 mm	1500
12.5 mm	2000
19.0 mm, OG 19.0 mm	3000
25.0 mm, OG 25.0 mm	4000

**10.0 PROCEDURES.**

**10.1 Method A - Centrifuge Extractor.**

**10.1.1 Method Specific Apparatus.** In addition to the apparatus listed in 5.0, the following apparatus is required for Method A.

- a) Centrifuge Extractor (AASHTO T 164)
- b) Filter rings, to fit the rim of the centrifuge bowl

**10.1.2 Centrifuge Extractor.**

- a) Dry the sample to constant weight (mass) in accordance with ITM 572
- b) Place the sample in a tared extraction bowl and determine the weight (mass)
- c) Cover the test sample in the bowl with Trichloroethylene and allow sufficient time for the solvent to break up the sample. The amount of solvent required shall be determined by the size of the centrifuge bowl.
- d) Assemble the centrifuge extractor with a dry weighed filter paper in place. Clamp the cover on tightly and place a container under the drain to collect the extracted solvent.
- e) Start the centrifuge revolving slowly and gradually increase the speed to a maximum of 3600 rpm, or until the solvent ceases to flow from the drain. Allow the extractor to stop and add solvent in accordance with 10.1.2 c. Repeat the procedure until the extracted solvent is a light straw color.
- f) Collect the extracted solvent in a suitable container
- g) Determine the amount of fines in the extracted solvent in accordance with AASHTO T 164 (11.6), except measurements shall be made to the nearest 0.1 g
- h) Dry the extracted aggregate and filter to a constant weight (mass) in the oven or skillet at  $221 \pm 9$  °F ( $105 \pm 5$  °C)

**10.1.3 Calculation Using Centrifuge.**

- a) The asphalt content in percent is calculated by the following formula:

$$\text{Asphalt Content, \%} = \frac{W_1 - (W_2 + W_3)}{W_1} \times 100$$

where:

$W_1$  = weight (mass) of sample, g

$W_2$  = weight (mass) of extracted aggregate, g

$W_3$  = weight (mass) of fines in extracted solvent, g

## **10.2 Method B - Vacuum Extractor.**

**10.2.1** Method Specific Apparatus. In addition to the apparatus listed in 5.0, the following apparatus is required for Method B:

- a) Vacuum extractor
- b) Filter paper, medium grade, fast filtering of the diameter required to fit the extractor, (Eaton-Dikeman #633-70)
- c) Vacuum pump
- d) Pan, round, bowl type, stainless steel
- e) No. 200 (75  $\mu$ m) sieve

### **10.2.2** Vacuum Extractor for Mixture without Fibers.

- a) Weigh approximately 50 g (record exact weight (mass)) of a filtering aid, such as celite, into a 1000 mL flask, add 500 mL of extraction solvent, and swirl until the filtering aid is completely in suspension. 100 g of filtering aid may be used if the solvent does not readily pass through the filter. Immediately pour the solution onto the filter. Start the vacuum pump and let the pump run until the pad formed by the filtering aid is surface dry and begins to crack slightly. Collect the solvent which goes through the filter in a flask, and pour the solvent onto the filter.
- b) Dry the sample to a constant weight (mass) in accordance with ITM 572. Determine the weight (mass) of a dry filter paper at  $221 \pm 9^{\circ}\text{F}$  ( $105 \pm 5^{\circ}\text{C}$ )
- c) If the sample is in an oven bag, remove the sample from the bag, and weigh the sample. Add enough solvent to cover the sample and stir vigorously (Note 1). Stirring shall continue until the sample is completely separated and essentially clean of the asphalt.

Note 1: Soaking the sample after stirring for several minutes may be beneficial in removing the asphalt from the aggregate. Extended soaking is acceptable only for aggregates with low water absorption values.

- d) Place a No. 200 (75  $\mu$ m) sieve on the filter of the extractor and start the vacuum pump

- e) Pour the solvent from the initial rinse onto the No. 200 (75  $\mu$ m) sieve. If the solvent does not readily pass through the filter, lightly scrape the celite to remove the fines. After the solvent has decanted through the filter, pour approximately 500 mL of solvent into the extractor and let this decant through the filter.
- f) Add 200 - 400 mL of solvent to the sample again and decant the solvent into the extractor. Repeat this procedure until the aggregate is clean of asphalt. Normally, approximately five rinses shall be needed to completely clean the sample (slag mixtures may require additional rinses.). Rinse the asphalt from the side of the extractor and the sieve with solvent.
- g) Allow the vacuum pump to run until all of the solvent has been decanted through the filter and the filter has a completely dry appearance.
- h) If the mixture of water and solvent forms a gel, replace the flask that has been used to collect the solvent and collect the water rinse separately.
- i) Gently stir the layer of celite to break the crust of fines which has formed on the pad. Caution is required to prevent tearing or puncturing the filter paper.
- j) Start the pump and pour water through the No. 200 (75  $\mu$ m) sieve to remove any film left from the solvent.
- k) Add enough water to cover the sample and stir well. The water will turn milky-white at this point. After completely stirring, pour the water through the No. 200 (75  $\mu$ m) sieve, start the vacuum pump, and decant the water into a flask.
- l) Repeat 10.2.2 k until the water is clear. Allow the vacuum pump to run until the filter pad is dry.
- m) Rinse the fines accumulated on the No. 200 (75  $\mu$ m) sieve into the extracted aggregate. Remove the filter ring and lift the filter and place the filter into another pan. Dry the filter to a constant weight (mass) in the oven or skillet at  $221 \pm 9^{\circ}\text{F}$  ( $105 \pm 5^{\circ}\text{C}$ ), and weigh immediately upon removal from the oven or skillet.
- n) Dry the extracted aggregate to a constant weight (mass) in the oven or skillet at  $221 \pm 9^{\circ}\text{F}$  ( $105 \pm 5^{\circ}\text{C}$ ), and weigh.

- o) The fines in the extracted solvent and water rinse shall be collected in accordance with 10.1.2 g.

**10.2.3** Calculation without Fibers. The asphalt content in percent is calculated by the following formula:

$$\text{Asphalt Content, \%} = \frac{W_1 - (W_2 - W_3)}{W_1} \times 100$$

where:

$W_1$  = weight (mass) of sample, g

$W_2$  = weight (mass) of extracted aggregate, g

$W_3$  = weight (mass) of fines in extracted solvent and water rinse, g

**10.2.4** Vacuum Extractor for Mixture with Fibers.

- a) The extraction procedure shall be conducted in accordance with 10.2.2.
- b) Rinse the fines and fibers accumulated on the No. 200 (75  $\mu$ m) sieve into the extracted aggregate
- c) Dry the extracted aggregate and fibers to a constant weight (mass) in the oven or skillet at  $221 \pm 9^\circ\text{F}$  ( $105 \pm 5^\circ\text{C}$ ), and weigh
- d) Remove the filter ring, lift the filter and place the filter into a separate bowl. Dry the filter in the oven or skillet at  $221 \pm 9^\circ\text{F}$  ( $105 \pm 5^\circ\text{C}$ ), and weigh immediately upon removal from the oven or skillet.
- e) Place the extracted aggregate and fibers into the necessary series of sieves. After shaking, the fibers shall be removed from the sieves.
- f) Place the fibers and three 1 in. (25 mm) washers into the series of sieves on the No. 4 (4.75 mm) sieve and shake for 10 minutes. Remove the fibers from the sieves and weigh separately.
- g) The extracted aggregate weight (mass) that is used to calculate the gradation may be determined by subtracting the weight (mass) of the fibers determined in 10.2.4 f from the combined weight (mass) of extracted aggregate and fibers in 10.2.4 c and weight (mass) of fines in 10.2.4 d.

- h)** The fines in the extracted solvent and water rinse shall be collected in accordance with 10.1.2 g.

#### **10.2.5 Calculation with Fibers.**

- a)** The asphalt content is calculated by the following formula:

$$\text{Asphalt Content, \%} = \frac{W_1 - (W_2 + W_3 + W_4)}{W_1} \times 100$$

where:

$W_1$  = weight (mass) of test sample, g

$W_2$  = weight (mass) of extracted aggregate, g

$W_3$  = weight (mass) of fines in extracted solvent and water rinse, g

$W_4$  = weight (mass) of fibers, g

- b)** The fiber content in the mixture is calculated by the following formula:

$$\text{Fiber Content, lbm/t (kg/Mg)} = \frac{W_4}{W_1} \times 2000 (1000)$$

### **10.3 Fines Correction Factor.**

- 10.3.1** The extraction procedure shall be performed in accordance with 10.2.2 or 10.2.4.

- 10.3.2** The fines in the extracted solvent and water rinse shall be collected in accordance with 10.1.2 g.

#### **10.3.3 Calculation with Fines Correction.**

- a)** A fines correction factor shall be determined by the following formula:

$$\text{Fines Correction Factor (C)} = \frac{W_3}{W_5}$$

where:

$W_3$  = weight (mass) of fines in extracted solvent and water rinse, g

$W_5$  = weight (mass) of extracted aggregate passing the No. 200 (75  $\mu$ m) sieve, g



- b) The fines correction factor shall be applied to each subsequent extraction test for each mixture. The correction factor is multiplied by the weight (mass) of extracted aggregate passing the No. 200 (75 µm) sieve, and the calculated weight (mass) is considered the fines in the extracted solvent and water rinse.
- c) The asphalt content in percent is calculated by the following formula:

$$\text{Asphalt Content, \%} + \frac{W_1 - (W_2 + (C \times W_5))}{W_1} \times 100$$

where:

C = fines correction factor

W<sub>1</sub> = weight (mass) of sample, g

W<sub>2</sub> = weight (mass) of extracted aggregate, g

W<sub>5</sub> = weight (mass) of extracted aggregate passing the No. 200 (75 µm) sieve, g

#### **10.4 Method C - Without Extractor.**

**10.4.1** Method Specific Apparatus. In addition to the apparatus listed in 5.0, the following apparatus is required for Method C:

- a) Pan, round, bowl type, stainless steel
- b) No. 200 (75 µm) sieve
- c) Suitable containers to collect the extracted solvent and water rinse

#### **10.4.2** Without Extractor.

- a) Dry the sample to a constant weight (mass) in accordance with ITM 572
- b) Add enough extraction solvent to cover the sample and stir vigorously (Note 1). Stirring shall continue until the sample is completely separated and essentially clean of the asphalt.

- c) Place a No. 200 (75  $\mu\text{m}$ ) sieve over the container (placing the No. 200 (75  $\mu\text{m}$ ) sieve in a large funnel prior to collecting the solvent in the container is beneficial)
- d) Pour the solvent from the initial rinse through the No. 200 (75  $\mu\text{m}$ ) sieve into the container
- e) Add 200 to 400 mL of solvent to the sample and again pour the solvent through the No. 200 (75  $\mu\text{m}$ ) sieve into the container. Repeat this procedure until the aggregate is clean of asphalt. Normally, approximately five rinses shall be required to completely clean the sample (slag mixtures may require additional rinses.). Rinse the asphalt from the sieve with the solvent.
- f) If the mixture of water and solvent form a gel, replace the container that has been used to collect the solvent, and collect the water rinse separately.
- g) Add enough water to cover the sample and stir well. The water shall turn milky-white at this point. After completely stirring, pour the water through the No. 200 (75  $\mu\text{m}$ ) sieve into the container.
- h) Repeat 10.4.2 g until the water is clear
- i) Rinse the fines accumulated on the No. 200 (75  $\mu\text{m}$ ) sieve into the extracted aggregate
- j) Dry the extracted aggregate to a constant weight (mass) in the oven or skillet at  $221 \pm 9^{\circ}\text{F}$  ( $105 \pm 5^{\circ}\text{C}$ ) and weigh
- k) The fines in the extracted solvent and water rinse shall be collected as in 10.1.2 g. If a high speed centrifuge is used, the extracted solvent and water rinse shall be poured through the centrifuge. The amount of material in the centrifuge cup(s) shall be verified to assure that the cup was not overloaded. If the cup was overloaded with fines, then an additional clean cup(s) shall be used, and the extracted solvent and water rinse shall be poured through the centrifuge again. This procedure is repeated until the cup is not overloaded.

**10.4.3** Calculation without Extractor. The asphalt content in percent is calculated by the following formula:

$$\text{Asphalt Content, \%} = \frac{W_1 - (W_2 + W_3)}{W_1} \times 100$$

where:

$W_1$  = weight (mass) of sample, g

$W_2$  = weight (mass) of extracted aggregate, g

$W_3$  = weight (mass) of fines in extracted solvent and water rinse, g

**11.0 GRADATION.** The gradation of the extracted aggregate shall be in accordance with AASHTO T 30 except that decantation through the No. 200 (75  $\mu$ m) sieve is not required. The entire sample of extracted aggregate is tested for gradation.

**12.0 REPORT.** The asphalt content and gradation are reported to the nearest 0.1% and the fiber content is reported to the nearest 0.1 lbm/t (0.05 kg/Mg).